

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
1 February 2001 (01.02.2001)

PCT

(10) International Publication Number
WO 01/08240 A1

(51) International Patent Classification⁷: H01L 51/20,
H05B 33/22

(21) International Application Number: PCT/CA00/00849

(22) International Filing Date: 21 July 2000 (21.07.2000)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
09/361,137 27 July 1999 (27.07.1999) US

(71) Applicant (for all designated States except US): LUX-
ELL TECHNOLOGIES INC. [CA/CA]; 5170A Timber-
lea Boulevard, Mississauga, Ontario L4W 2S5 (CA).

(72) Inventors; and

(75) Inventors/Applicants (for US only): HOFSTRA, Peter,

G. [CA/CA]; 94 Steffler Drive, Guelph, Ontario N1G 3J9
(CA). KRASNOV, Alexey [UA/CA]; 802 Clark Boulevard,
Apt. 227, Brampton, Ontario L6T 2E8 (CA).


(74) Agents: NASSIF, Omar, A. et al.; Gowling Lafleur Hen-
derson LLP, Suite 4900, Commerce Court West, Toronto,
Ontario M5L 1J3 (CA).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CR, CU, CZ,
DE, DK, DM, DZ, EE, ES, FI, GB, GD, GE, GH, GM, HR,
HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR,
LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ,
NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM,
TR, TT, TZ, UA, UG, US, UZ, VN, YU, ZA, ZW.

(84) Designated States (regional): ARIPO patent (GH, GM,
KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZW), Eurasian
patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European
patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE,

[Continued on next page]

(54) Title: ORGANIC ELECTROLUMINESCENT DEVICE



(57) Abstract: The present invention provides a novel organic electroluminescent device having an optical interference member which reduces the overall reflectance from the device. The invention is particularly suited to current-driven organic displays having an anode, an electroluminescent layer and a cathode, where at least one optical interference member is placed between two of the layers and thus forms part of the electrical circuit required to excite the display. The optical interference member is chosen to have a thickness which causes at least some destructive optical interference of ambient light incident on the display. In addition, the material(s) of the optical interference member are chosen to have a work function which is compatible with the highest occupied molecular orbital, or the lowest unoccupied molecular orbital of the electroluminescent layer, depending on the location of the optical interference member in relation to the anode, cathode and electroluminescent layer. The appropriate selection of material can ensure proper current flow through the device, thus reducing the likelihood of electrical breakdown of the organic electroluminescent layer, and improving the overall energy efficiency of the device.

WO 01/08240 A1



IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).

For two-letter codes and other abbreviations, refer to the "Guidance Notes on Codes and Abbreviations" appearing at the beginning of each regular issue of the PCT Gazette.

Published:

- *With international search report.*
- *Before the expiration of the time limit for amending the claims and to be republished in the event of receipt of amendments.*

-1-

ORGANIC ELECTROLUMINESCENT DEVICETECHNICAL FIELD

The present invention relates generally electroluminescent devices and
5 more specifically relates to an organic electroluminescent device having a thin
film optical interference layer to reduce reflectance from ambient light.

BACKGROUND ART

Electroluminescent devices (ELDs) are well known and are generally
10 constructed of several layers of different materials. These layers typically consist
of a transparent front-electrode layer, an electroluminescent layer and a back-
electrode layer. When a voltage is applied across the electrodes, the
electroluminescent layer becomes active, converting some portion of the
electrical energy passing therethrough into light. This light is then emitted out
15 through the front-electrode, which is transparent to the emitted light, where it is
visible to a user of the device.

Electroluminescent devices can be particularly useful as computer
displays and are generally recognized as high-quality displays for computers and
other electronic devices used in demanding applications such as military, avionics
20 and aerospace where features such as high reliability, low weight, and low power
consumption are important. Electroluminescent displays are also gaining
recognition for their qualities in automotive, personal computer and other
consumer industries, as they can offer certain benefits over other displays such
as cathode-ray tubes ("CRT") and liquid crystal displays ("LCD").

25 One feature of electroluminescent displays is the ability to add thin films
between the layers to vary the characteristics of the display. It is known to use
thin film layers in electroluminescent displays to improve selected display
characteristics, such as signal-to-reflected-ambient light ratio ("SRA") and
contrast ratio ("CR"). For greater clarity, signal-to-reflected ambient light ratio
30 can be defined as:

-2-

$$SRA = \frac{L_{em}}{R \times L_{amb}}$$

5

where:

SRA = Signal-to-reflected ambient light ratio,

L_{em} = Emitted luminance of the device,

10 R = Reflectance of the device, and

L_{amb} = The ambient illuminance, or the ambient light incident on the display,

and, in a pixilated device, contrast ratio can be defined as:

15

$$CR = \frac{L_{on} + R \times L_{amb}}{L_{off} + R \times L_{amb}}$$

where:

20 CR = Contrast Ratio,

L_{on} = Emitted luminance of active or "on" pixels,

L_{off} = Emitted luminance of inactive or "off" pixels,

R = Reflectance of the device, and

25 L_{amb} = The ambient illuminance, or the ambient light incident on the display.

One particular type of thin-film layer that can be used to improve contrast ratio in electroluminescent devices is a substantially transparent optical interference layer placed between one or more of the layers of the electroluminescent device, as taught in United States patent 5,049,780 [Dobrowolski]. As will be apparent to those of skill in the art, improvements to the contrast ratio of an electroluminescent device is generally desirable and

30

-3-

particularly important in avionics and military applications where poor contrast and glare can have serious consequences. Using the principle of destructive interference, the optical interference layer can result in the reduction of the amplitude of ambient light by superimposing of two or more, out-of-phase, electromagnetic waves, which can be generated by reflection and/or transmission at the interfaces of thin-film layer(s). By selecting appropriate thicknesses of the layers, optical destructive interference at the electromagnetic wavelengths of interest (typically visible ambient light waves reflected off of the display) can result in an exceptional contrast ratio and/or signal-to-reflected ambient light ratio.

Dobrowolski is generally directed to voltage-driven inorganic electroluminescent devices, where the electroluminescent layer is formed of an inorganic material, and which typically require one or more additional transparent dielectric layers to reduce electrical-breakdown of the inorganic electroluminescent layer. Such inorganic electroluminescent devices are typically voltage-driven, powered with alternating current ("ac") in order to reduce charge build-up within the device. While Dobrowolski does generally contemplate the use of direct current ("dc") electroluminescent devices without transparent dielectric layers, such inorganic devices are still voltage-driven, and are generally prone to electrical breakdown of the electroluminescent layer.

With the advent of modern current-driven organic electroluminescent devices which offer certain advantages (such as colour improvements and a reduced barrier to current flow to reduce the necessary drive voltage) compared to voltage-driven inorganic electroluminescent devices, there is now a need to improve the contrast ratio and/or signal to ambient light ratio of these organic devices, and it can be seen that the prior art does not teach a suitable optical interference electroluminescent device to address this need.

DISCLOSURE OF THE INVENTION

It is therefore an object of the present invention to provide a novel organic electroluminescent device which obviates or mitigates at least one of the disadvantages of the prior art.

-4-

In an embodiment of the invention there is provided an optical interference electroluminescent device for displaying an image to a viewer in front of the device, comprising: an anode layer; a cathode layer, at least one of the anode layer and the cathode layer being substantially transparent to at least a portion of emitted electroluminescent light; at least one organic electroluminescent layer disposed between the anode layer and the cathode layer, the electroluminescent layer having a first energy characteristic being the amount of energy required to extract an electron from a highest occupied molecular orbital of the electroluminescent layer, and a second energy characteristic being the amount of energy required to extract an electron from a lowest unoccupied molecular orbital of the electroluminescent layer; and at least one optical interference member disposed between two of the layers, and having a work function substantially equal to the first energy characteristic when the optical interference member is between the anode and the electroluminescent layer, and having a work function substantially equal to the second energy characteristic when the optical interference member is between the cathode and the electroluminescent layer, the optical interference member being of a thickness and material such that the spectral reflectance of the electroluminescent device is so modified that the reflectance of ambient light by the electroluminescent device towards the viewer is reduced.

In another embodiment of the invention, there is provided an electroluminescent device to emit light in a selected spectrum, comprising: an anode layer, a cathode layer, wherein one of the anode layer and the cathode layer are substantially transparent to at least a portion of the selected spectrum emitted by the electroluminescent device. The electroluminescent device further comprises an organic electroluminescent layer between the anode layer and the cathode layer, the electroluminescent layer having a highest occupied molecular orbital respective to the anode layer and having a lowest unoccupied molecular orbital respective to the cathode layer. The device further includes an optical interference member having a selected work function and operable to reduce ambient light reflected through the transparent layer, the optical interference member being between the electroluminescent layer and one of the anode layer

-5-

and the cathode layer, wherein the difference between the selected work function and an energy level required to extract an electron from a respective molecular orbital approaches zero.

In another embodiment of the invention, there is provided a method of fabricating an electroluminescent device for displaying an image to a viewer in front of the device, comprising the steps of:

- depositing an anode layer onto a substrate;
- depositing an organic electroluminescent layer onto the anode layer, the electroluminescent layer having a first energy characteristic associated with an anode side, and a second energy characteristic associated with a cathode side;
- depositing an optical interference member onto the electroluminescent layer, the optical interference member for reducing the reflectance of ambient light towards the viewer, the optical interference member having a work function substantially equal to the second energy characteristic;
- depositing a cathode layer onto the optical interference member; and
- sealing the device.

In another embodiment of the invention there is provided a method of assembling an electroluminescent device for displaying an image to a viewer in front of the device, comprising the steps of:

- depositing an anode layer onto a substrate;
- depositing an optical interference member onto the anode layer; the optical interference member for reducing the reflectance of ambient light towards the viewer, the optical interference member having a work function;
- depositing an organic electroluminescent layer onto the interference member, the electroluminescent layer having an energy characteristic being the amount of energy required to extract an electron from the electroluminescent layer, the energy characteristic being substantially equal to the work function;
- depositing a cathode layer onto the electroluminescent layer; and
- sealing the device.

In another embodiment of the invention, there is provided a method of displaying an image to a viewer comprising the steps of:

-6-

emitting light from an organic electroluminescent layer between an anode and a cathode, said electroluminescent layer having a first energy characteristic respective to said anode and a second energy characteristic respective to said cathode;

5 receiving ambient light incident towards said electroluminescent layer; and

forming destructive interference from said ambient light at the incident surface of an optical interference member, said optical interference member having a selected work function and disposed between said electroluminescent
10 layer and one of said anode and said cathode, the difference between said work function and a respective energy characteristic approaching zero.

The appropriate selection of material of the at least one optical interference member ensures proper current flow through the device, thus reducing the likelihood of electrical breakdown of the organic electroluminescent
15 layer, and improving the overall energy efficiency of the device, while still reducing reflectance towards a viewer.

BRIEF DESCRIPTION OF THE DRAWINGS

Embodiments of the present invention will be described with reference to
20 the accompanying drawings, in which:

Figure 1 is a schematic diagram of a cross-section of through a portion of an optical interference organic electroluminescent device in accordance with a first embodiment of the invention; and

Figure 2 is a schematic diagram of a cross-section of through a portion of
25 an optical interference organic electroluminescent display in accordance with a second embodiment of the invention.

BEST MODE FOR CARRYING OUT THE INVENTION

Referring now to Figure 1, an electroluminescent device in accordance
30 with a first embodiment of the invention is indicated generally at 10. Device 10 comprises an electroluminescent transmitting anode 12, an electroluminescent layer 14 disposed behind anode 12, an optical interference member 16 disposed

-7-

behind the electroluminescent layer 14 and a cathode 18 disposed behind the interference member 16. Device 10 is connected to a current source 20 via anode 12 and cathode 18 in order to drive a constant current through device 10.

Electroluminescent transmitting anode 12 is any conducting material
5 which is transparent to at least a portion of emitted electroluminescent light, such as indium tin oxide (ITO) or zinc oxide (ZnO). In a present embodiment, anode 12 is a layer of indium tin oxide preferably having a thickness of about fifteen-hundred angstroms (1500Å).

It is to be understood that electroluminescent transmitting anode 12 can
10 have different thicknesses, and can be in the range of, for example, from about one-thousand angstroms (1000Å) to about three-thousand angstroms (3000Å), or from about twelve-hundred angstroms (1200Å) to about two-thousand angstroms (2000Å).

Electroluminescent layer 14 is an organic electroluminescent material
15 such as tris(8-quinolinolato aluminum) (Alq3) or poly(n-vinyl carbazole) (PVC₂) wherein photons of light are emitted when electrons drop from a lowest unoccupied molecular orbital ("lumo") of layer 14, where they combine with holes in the highest occupied molecular orbital ("homo") of layer 14. Accordingly, a current flow through electroluminescent layer 14 can produce an
20 emission of light. In a present embodiment, layer 14 is preferably made from tris(8-quinolinolato aluminum), preferably having a thickness of about one-thousand angstroms (1000Å), although those of skill in the art will be able to select other appropriate thicknesses of this layer. As is known to those familiar with the electrical properties of tris(8-quinolinolato aluminum), the energy
25 required to extract an electron from the highest occupied molecular orbital, E_{HOMO} , is about 5.4 electron-volts, which can also be described as the energy required to extract an electron from the surface of layer 14, or, the work function of layer 14. Further, the energy required to extract an electron from the lowest unoccupied molecular orbital of tris(8-quinolinolato aluminum) is about 3.0
30 electron-volts, which can be referred to as E_{LUMO} . Thus the difference between E_{HOMO} and E_{LUMO} of tris(8-quinolinolato aluminum) is about 2.4 electron-volts. In other embodiments of the invention, other organic materials can be so chosen

-8-

(i.e. by selection of material or modification of material with dopants) so that the difference between E_{HOMO} and E_{LUMO} is in the range from about 1.5 electron-volts to about 3.0 electron-volts, which covers the spectrum of visible light.

In a present embodiment, optical interference member 16 comprises a
5 semi-absorbent layer 16a and a transparent layer 16b. Semi-absorbent layer 16a is partially reflective, partially absorbing and partially transmissive of light in the visible spectrum, and in a present embodiment, is made from magnesium silver (Mg:Ag) having a thickness of about one-hundred-and-eighty-five angstroms (185Å). Other suitable materials can include Inconel™, Nickel (Ni), Titanium,
10 or a suitable organic material and appropriate thicknesses of such layers can be determined by those of skill in the art. The extinction coefficient of the material and its thickness, should be selected so that the reflection from layer 16a at a preselected wavelength, neglecting optical interference, should preferably be at least about thirty-five percent, with the remainder of light energy being,
15 transmitted or absorbed, and dissipated in the form of heat. Similarly, transmission through layer 16a at a preselected wavelength, neglecting optical interference, will preferably be at least about thirty-five percent.

It is to be understood that the extinction coefficient of layer 16a and its thickness can be selected so that the transmission through layer 16a at a
20 preselected wavelength, neglecting optical interference, can be from about thirty percent to about forty percent. Overall, the amount of light transmitted through layer 16a, after two passes, should be substantially equal to the amount of light that is originally reflected from layer 16a, in order to achieve the appropriate destructive interference at the reflective surface of layer 16a, as will be
25 understood by those of skill in the art.

Substantially transparent conducting layer 16b is made from indium tin oxide (ITO) and has a thickness of about eight-hundred-and-forty angstroms (840Å). Other suitable materials and layer thicknesses can be used as will occur to those of skill in the art, such as zinc oxide (ZnO). The extinction coefficient
30 of the material of layer 16b and its thickness is selected so that the transmission through layer 16b at a preselected wavelength, neglecting optical interference, is greater than about eighty percent, but is preferably at least about ninety percent.

As known to those of skill in the art, it is generally preferred that the preselected wavelength(s) for layer 16b should be substantially equal to the preselected wavelengths used to choose layer 16a.

A wavelength of about five-hundred-and-fifty nanometers (550nm), the centre of the spectrum of visible light, is a presently preferred preselected wavelength used for the purpose of determining appropriate thicknesses and materials of layers 12 and 14 and member 16, as the resulting device 10 can have the desired optical interference characteristics across the visible light spectrum. As will be understood by those of skill in the art, an incidental benefit to the selection of this wavelength can result in a device which reflects electromagnetic energy outside the visible spectrum, including infra-red, thus reducing the heating of the display. However, it will occur to those of skill in the art that other wavelengths can be selected, as desired.

Optical interference member 16 is also quantifiable in terms of its work function Φ_{OIM} , or the amount of energy required to extract an electron from the surface of member 16. In a present embodiment, positive-charges or holes flow from current source 20 through anode 12 and into electroluminescent layer 14, where they combine with electrons which flow from current source 20 through cathode 18, optical interference member 16 and into electroluminescent layer 14. Thus, in order to facilitate the injection of electrons into the lowest unoccupied molecular orbital of layer 14, the materials chosen for member 16 are such that the difference X between E_{LUMO} and Φ_{OIM} , expressed as an absolute value, approaches zero. This expression can be expressed mathematically as:

$$X = |\Phi_{OIM} - E_{LUMO}|$$

Where $\lim_{X \rightarrow 0}$

In order for the difference X to approach zero, it is believed that the X can be in the range of from about 0.0 to about 1.5 electron-volts (eV). It is

-10-

believed that the difference X can be in the range of from about 0.1 to about 1.3 electron-volts. More preferably, it is believed that the difference X should be in the range of from about 0.6 to about 1.0 electron-volts. In the present embodiment, where layer 16a is made from magnesium silver and layer 16b is made from indium tin oxide, the overall work function Φ_{OM} of member 16 is about 3.6 electron-volts. As E_{LUMO} is about 3.0 electron-volts, the difference X is about 0.6 electron-volts.

Cathode 18 is magnesium silver having a thickness of about five-hundred angstroms (500Å), and in the present embodiment is reflective. In other embodiments, it is believed that cathode 18 can have a thickness between about two-hundred-and-fifty angstroms (250Å) to about two-thousand-angstroms (2000Å). However, it will occur to those of skill in the art that other suitable conducting materials and thicknesses can be used.

It now will be apparent that the thickness and material(s) of member 16 and its components can be determined with an operation that considers, at least in part, the thicknesses of and/or materials of anode 12, electroluminescent layer 14, and cathode 18.

Device 10 can be fabricated using techniques known in the art. In the foregoing embodiment, anode 12 is vacuum-deposited onto a glass substrate, and the subsequent layers are formed thereon also using vacuum deposition. The entire device 10 is then sealed using techniques known in the art. Other suitable substrates and means of fabricating device 10 will occur to those of skill in the art. For example, the substrate can be plastic. Further, where electroluminescent layer 14 is poly(n-vinyl carbazole), then spin-coating can be an appropriate fabrication technique for layer 14.

The operation of device 10 will now be discussed. It will be appreciated by those of skill in the art that the following is a simplified model for purposes of explanation, and that other physical phenomena occurring during the operation of device 10 are assumed, for the purposes of this discussion, to have a negligible influence on the operation. Current source 20 is 'on', so that holes are driven into electroluminescent layer 14 via anode 12. These holes then combine with electrons delivered into layer 14 from source 20, via cathode 18 and optical

-11-

interference member 16. The fact that the difference between E_{LUMO} and Φ_{OIM} , expressed as an absolute value, approaches zero, reduces barriers to current flow through device 10, preventing or inhibiting breakdown of layer 14. The recombination of holes and electrons in layer 14 causes light to be emitted out through the front or exterior face of anode 12 and towards a viewer, as indicated by arrow L_{em} .

At the same time, ambient light is incident upon device 10, as indicated by arrow L_{amb} and passes through anode 12 and electroluminescent layer 14. Ambient light L_{amb} incident upon semi-absorbing layer 16a is partially reflected, partially absorbed and partially transmitted. The light transmitted through semi-absorbing layer 16a passes through transparent layer 16b, where it reflects off cathode 18 and back through transparent layer 16b, at which point this reflected light is inverted one-hundred-and-eighty degrees out of phase with the partially reflected light from layer 16a, and thus these two reflections destructively interfere and substantially cancel each other out. The energy otherwise found in these two reflections is absorbed by semi-absorbing layer 16a and cathode 18, where it is dissipated as a relatively small amount of heat. The result is that reflected light (L_{ref}) back towards the viewer from device 10 is reduced. In a present embodiment, reflected light (L_{ref}) is reduced by about ninety percent, compared to an electroluminescent device assembled without optical interference member 16.

It is believed that in other embodiments of the invention, reflected light (L_{ref}) can be reduced by as much as about 99.5 percent by choosing different materials, thicknesses and extinction coefficients for optical interference member 16 and by selected appropriate thicknesses and materials for the other layers in device 10, although still within the aforementioned acceptable parameters and ranges such that the difference between E_{LUMO} and Φ_{OIM} , expressed as an absolute value, approaches zero. However, while a higher difference in energy levels between E_{LUMO} and Φ_{OIM} , still within the acceptable ranges, can achieve reduced reflection, it can also result in reduced electrical efficiency in the current flow through device 10.

-12-

In other embodiments of the invention, a suitably modified optical interference member 16 can be disposed in series with other layers of device 10. Referring now to Figure 2, an electroluminescent device in accordance with a second embodiment of the invention is indicated generally at 10a. Like components to those shown in Figure 1 are indicated with like reference numbers. Device 10a comprises a electroluminescent transmitting anode 12, an optical interference member 16' disposed behind anode 12, an electroluminescent layer 14 disposed behind interference member 16', and a cathode 18 disposed behind electroluminescent layer 14. Device 10a is connected to a current source 20 via anode 12 and cathode 18 in order to drive a constant current through device 10 and layer 14.

Electroluminescent transmitting anode 12 is any conducting material which is transparent to at least a portion of emitted electroluminescent light, such as indium tin oxide (ITO) or zinc oxide (ZnO). In a present embodiment, anode 12 is a layer of indium tin oxide preferably having a thickness of about fifteen-hundred angstroms (1500Å).

It is to be understood that electroluminescent transmitting anode 12 can have different thicknesses, and can be in the range of, for example, from about one-thousand angstroms (1000Å) to about three-thousand angstroms (3000Å), or from about twelve-hundred angstroms (1200Å) to about two-thousand angstroms (2000Å).

Electroluminescent layer 14 is an organic electroluminescent material such as tris(8-quinolinolato aluminum) (Alq3) or poly(n-vinyl carbazole) (PVC₂) wherein photons of light are emitted when electrons drop from a lowest unoccupied molecular orbital ("lumo") of layer 14, where they combine with holes in the highest occupied molecular orbital ("homo") of layer 14. Accordingly, a current flow through electroluminescent layer 14 can produce an emission of light. In a present embodiment, layer 14 is preferably made from tris(8-quinolinolato aluminum), preferably having a thickness of about one-thousand angstroms (1000Å), although those of skill in the art will be able to select other appropriate thicknesses of this layer. As is known to those familiar with the electrical properties of tris(8-quinolinolato aluminum), the energy

-13-

required to extract an electron from the highest occupied molecular orbital, E_{HOMO} , is about 5.4 electron-volts, which can also be described as the energy required to extract an electron from the surface of layer 14, or, the work function of layer 14. Further, the energy required to extract an electron from the lowest unoccupied molecular orbital of tris(8-quinolinolato aluminum) is about 3.0 electron-volts, which can be referred to as E_{LUMO} . Thus the difference between E_{HOMO} and E_{LUMO} of tris(8-quinolinolato aluminum) is about 2.4 electron-volts. In other embodiments of the invention, other organic materials can be so chosen (i.e. by selection of material or modification of material with dopants) so that the difference between E_{HOMO} and E_{LUMO} is in the range from about 1.5 electron-volts to about 3.0 electron-volts, which covers the spectrum of visible light.

In a present embodiment optical interference member 16' comprises a substantially transparent conducting layer 16c made from indium tin oxide (ITO) and having a thickness of about seven-hundred-and-forty-five angstroms (745Å). Other suitable materials can be used as will occur to those of skill in the art, such as zinc oxide (ZnO) or a suitable organic material. The indium tin oxide of layer 16c is modified (by controlling its stoichiometry) so that it behaves as a quarter-wave-stack at a light wavelength of five-hundred-and-fifty nanometers (550 nm), and chosen so that the transmission through layer 16c is greater than about eighty percent, and preferably at least about ninety percent. However, it will occur to those of skill in the art that other wavelengths can be selected, as desired.

As discussed previously, optical interference member 16' is also measurable in terms of work function Φ_{OIM} . In a present embodiment, holes flow from current source 20 through anode 12 and optical interference member 16', and into electroluminescent layer 14, where they combine with electrons which flow from current source 20 through cathode 18 and into electroluminescent layer 14. Thus, in order to facilitate the extraction of electrons from the highest occupied molecular orbital of electroluminescent layer 14, the materials chosen for member 16' are such that the difference γ between E_{HOMO} and Φ_{OIM} , expressed as an absolute value, approaches zero. This expression can be expressed mathematically as:

-14-

$$Y = |\Phi_{OIM} - E_{HOMO}|$$

$$\text{Where } \lim_{Y \rightarrow 0}$$

In order for the difference between E_{HOMO} and Φ_{OIM} to approach zero, it is believed that the difference Y can be in the range of from about 0.0 to about 1.5 electron-volts (eV). It is believed that the difference Y can be in the range of
5 from about 0.1 to about 1.3 electron-volts. More preferably, it is believed that the difference Y should be in the range of from about 0.4 to about 1.0 electron-volts. In the present embodiment, where layer 16a is made from magnesium silver and layer 16b is made from indium tin oxide, the overall work function Φ_{OIM} of member 16 is about 5.0 electron-volts. Since E_{HOMO} is about 5.4 electron-volts,
10 the difference Y is about 0.4 electron-volts (eV).

Cathode 18 is magnesium silver having a thickness of about five-hundred angstroms (500Å), and in the present embodiment is reflective. In other embodiments, it is believed that cathode 18 can have a thickness between about two-hundred-and-fifty angstroms (250Å) to about two-thousand-angstroms
15 (2000Å). However, it will occur to those of skill in the art that other suitable conducting materials and thicknesses can be used.

It now will be apparent that the thickness and material(s) of member 16' and its components can be determined with an operation that considers, at least in part, the thicknesses of and/or materials of anode 12, electroluminescent layer
20 14, and cathode 18.

Device 10a can be fabricated using techniques known in the art. In the foregoing embodiment, anode 12 is vacuum-deposited onto a glass substrate, and the subsequent layers are formed thereon also using vacuum deposition. The entire device 10a is then sealed using techniques known in the art. Other suitable
25 substrates and means of fabricating device 10a will occur to those of skill in the art. For example, the substrate can be plastic. Further, where electroluminescent

-15-

layer 14 is poly(n-vinyl carbazole), then spin-coating can be an appropriate fabrication technique for layer 14.

The operation of device 10a will now be discussed. It will be appreciated by those of skill in the art that the following is a simplified model for purposes of explanation, and that other physical phenomena occurring during the operation of device 10a are assumed to have a negligible influence on the operation. Current source 20 is 'on', so that holes or positive-charges are driven into electroluminescent layer 14 via anode 12 and optical interference member 16. These positive-charges then combine with electrons delivered into layer 14 from source 20 via cathode 18. Because the difference between E_{HOMO} and Φ_{OIM} approaches zero, barriers to current flow through device 10a are reduced, preventing or inhibiting breakdown of layer 14. The recombination of electrons and holes in layer 14 causes light to be emitted out through the front face of anode 12 and towards a viewer, as indicated by arrow L_{em} .

At the same time, ambient light is incident upon device 10a as indicated by arrow L_{amb} and passes through anode 12 and is incident upon transparent layer 16c. About half of ambient light L_{amb} incident upon layer 16c is reflected, while the remainder is transmitted. The light transmitted through layer 16c reflects off the surface of electroluminescent layer 14 and back through layer 16c. Due to the quarter-wavelength thickness of layer 16c, this reflected light from layer 14 is inverted one-hundred-and-eighty degrees out of phase with the reflected light from layer 16c, and thus these two reflections destructively interfere and substantially cancel each other out. The energy otherwise found in these two reflections is transmitted through layer 16c. The result is that reflected light (L_{ref}) back towards the viewer from device 10 is reduced. In the present embodiment, reflected light (L_{ref}) is believed to be reduced by a range of from about 0.5 percent to about two percent, compared to electroluminescent devices without layer 16'.

While only specific combinations of the various features and components of the present invention have been discussed herein, it will be apparent to those of skill in the art that desired sub-sets of the disclosed features and components and/or alternative combinations of these features and components can be utilized, as desired. For example, the embodiments discussed herein can be combined to

-16-

provide multiple optical interference members disposed between different layers of the electroluminescent device, and therefore disjoined from each other, in order to further reduce reflectance from the device. For example, layer 16' and layer 16 can be included on respective sides of layer 14.

5 Furthermore, each optical interference member can be a transparent layer or a combination of a transparent layer and a semi-absorbing layer in order to achieve different results, and it will be apparent that these different types of optical interference members can also be placed at different locations throughout the device. For example, it is contemplated that a transparent layer, without a
10 semi-absorbing layer can be used between the organic electroluminescent layer and the cathode, and similarly, a combination of a transparent layer and a semi-absorbing layer can be used between the anode and the electroluminescent layer, by having the difference between work function of the optical interference member and the energy required to extract an electron from either highest
15 occupied molecular orbital, and/or the lowest unoccupied molecular orbital, approach zero, as appropriate.

 The present invention can be suitable for a computer display. For example, a pixilated organic electroluminescent computer display can be formed where the anode comprises a plurality of generally parallel and spaced anodes to
20 compose the front layer of an organic electroluminescent computer display, and the cathode comprises a number of spaced cathodes which are generally perpendicular to the anodes. It will be further understood that the anode and the cathode can be patterned in a variety of ways, other than pixilated, to create different recognizable patterns to a user of device 10. When such a display is
25 pixilated or patterned, it will be appreciated that individual pixels or patterns can be fired using known techniques such as pulsed-DC, and/or adding a periodic reverse-polarity 'refresh' pulse to reduce built-up charge. The device can also be hybrid-display having an active matrix, as can be found in notebook computers.

 In addition, the present invention can be suitably modified for use in
30 colour organic electroluminescent devices. As known to those of skill in the art, such multi-colour and full-colour devices can be formed from stacked transparent organic electroluminescent layers. Where the optical interference member is

-17-

between two of these stacked layers, it will be apparent that the difference between its work function and the energy level required to extract an electron from the lowest unoccupied molecular orbital of the electroluminescent layer nearest the anode should approach zero, and the difference between the work
5 function and the energy level required to extract an electron from the highest occupied molecular orbital of the electroluminescent layer nearest the cathode should also approach zero. More preferably, the work function of the optical interference member should be the average of the lowest unoccupied molecular orbitals of the surrounding electroluminescent layers.

10 Multi-coloured and full-coloured devices can also be provided through a patterned red-green-blue organic layer (i.e. by selecting materials having inherent colour properties, or by appropriately doping the patterns on the layer). Other colourizing techniques can including the use of a white-emitter and appropriate filters. It will be apparent that the teachings of the present invention can be
15 modified to accommodate these and other colour devices.

The present invention can also be used as a backlight for a liquid crystal display. It will also be understood that the present invention can be suitably modified for organic electroluminescent devices which have an electron transport layer between the cathode and the electroluminescent layer, and/or a hole
20 transport layer between the anode and the electroluminescent layer. In this embodiment, the optical interference member can thus be placed between the transport layer and the electroluminescent layer, or the transport layer can be placed between the electroluminescent layer and the optical interference member. In this embodiment of the invention, it will be apparent that the optical
25 interference member is still selected to have a work function such that the difference between the work function and the energy levels associated with the respective anode side and/or cathode side of the electroluminescent layer(s) approach zero, in order to facilitate current flow through the entire device. It is also contemplated that an appropriate transport layer can be incorporated into an
30 optical interference member.

Furthermore, while the embodiments herein refer to a front anode and a rear cathode, it will be apparent that the present invention can be suitable to a

-18-

device having a front cathode and a rear anode, as long as at least the front layer is transparent to at least a portion of emitted electroluminescent light.

The present invention provides a novel organic electroluminescent device having an optical interference member which reduces the overall reflectance from the device. The optical interference member is selected to have a thickness which
5 causes at least some destructive optical interference of ambient light incident on the display. In addition, the material(s) of the optical interference member are chosen to have a work function such that the difference between the work function and the energy level required to extract an electron from the highest
10 occupied molecular orbital, or the lowest unoccupied molecular orbital of the electroluminescent layer approaches zero, depending on the direction of current flow and location of the optical interference member in relation to the electroluminescent layer. The appropriate selection of material for the optical interference member improves proper current flow through the device, thus
15 reducing the likelihood of electrical breakdown of the organic electroluminescent layer and improving the overall energy efficiency of the device. Finally, in embodiments where a semi-absorbent layer and transparent layer are combined to form the optical interference member, then placement of such an optical interference member in contact with the electrode at the back of the device can
20 actually increase the reflectance of infra-red ambient signatures, compared to absorbing films, thus reducing the heating of the display and reducing the likelihood of damage to the electroluminescent layer.

While the present invention has been described with reference to preferred
25 and specifically illustrated embodiments, it will of course be understood by those skilled in the arts that various modifications to these preferred and illustrated embodiments may be made without departing from the spirit and scope of the invention.

All publications, patents and patent applications referred to herein are
30 incorporated by reference in their entirety to the same extent as if each individual publication, patent or patent application was specifically and individually indicated to be incorporated by reference in its entirety.

-19-

What is claimed is:

1. An electroluminescent device for displaying an image to a viewer in front of said device, comprising:
 - an anode layer;
 - a cathode layer, at least one of said anode layer and said cathode layer being said front and being substantially transparent to electroluminescent light;
 - an organic electroluminescent layer disposed between said cathode layer and said anode layer, said electroluminescent layer having a highest occupied molecular orbital associated with an anode side, and a lowest unoccupied molecular orbital associated with a cathode side; and
 - an optical interference member for reducing the reflectance of ambient light towards said viewer, said member disposed between said anode layer and said cathode layer, said optical interference member having a work function, such that a first difference between said work function and a first energy level required to remove an electron from said highest occupied molecular orbital when said optical interference member is at said anode side approaches zero, and a second difference between said work function and a second energy level required to remove an electron from said lowest unoccupied molecular orbital when said optical interference member is at said cathode side approaches zero.
2. The device according to claim 1, wherein said first difference is from about zero electron-volts to about 1.5 electron-volts.
3. The device according to claim 1, wherein said first difference is from about 0.1 electron-volts to about 1.3 electron-volts.
4. The device according to claim 1, wherein said first difference is from about 0.4 electron-volts to about one electron-volt.
5. The device according to claim 1, wherein said first energy level is about 5.4 electron-volts and said work function is about 5.0 electron-volts.

-20-

6. The device according to claim 1, wherein said second difference between said work function and said second energy characteristic is from about zero electron-volts to about 1.5 electron-volts.
7. The device according to claim 1, wherein said second difference is from about 0.1 electron-volts to about 1.3 electron-volts.
8. The device according to claim 1, wherein said second difference is from about 0.6 electron-volts to about one electron-volt.
9. The device according to claim 1, wherein said second energy level is about 3.0 electron-volts and said work function is about 3.6 electron-volts.
10. The device according to claim 1, wherein said organic electroluminescent layer is tris(8-quinolinolato aluminum).
11. The device according to claim 1, wherein said organic electroluminescent layer is poly(n-vinyl carbozale).
12. The device according to claim 1, wherein said optical interference member is between said electroluminescent layer and said cathode.
13. The device according to claim 1, wherein said optical interference member comprises a semi-absorbent layer and a transparent layer.
14. The device according to claim 13, wherein said semi-absorbent layer is magnesium silver and said transparent layer is indium tin oxide, said optical interference member having a work function of 3.6 electron-volts.
15. The device according to claim 1, wherein said optical interference member is between said anode and said electroluminescent layer.

-21-

16. The device according to claim 1, wherein said optical interference member comprises a transparent layer.
17. The device according to claim 16, wherein said transparent layer is made from indium tin oxide.
18. The device according to claim 1, further comprising at least one additional optical interference member disposed between said anode layer and said cathode layer and disjoined from said optical interference member.
19. The device according to claim 1, further comprising at least one additional organic electroluminescent layer disposed between said cathode layer and said anode layer.
20. The device according to claim 19, wherein said optical interference member is between two of said electroluminescent layers.
21. The device according to claim 1, wherein said device is a patterned organic electroluminescent computer display.
22. The device according to claim 21, wherein said device is pixilated and said anode comprises a plurality of generally parallel anodes and said cathode comprises a plurality of cathodes that are generally perpendicular to each of said plurality of generally parallel anodes.
23. The device according to claim 1, wherein said device is a colour electroluminescent display.
24. The device according to claim 1, further comprising an electron transport layer between said cathode layer and said electroluminescent layer.

-22-

25. The device according to claim 1, further comprising a hole transport layer between said anode layer and said electroluminescent layer.

26. The device according to claim 25, wherein said hole transport layer is incorporated into said optical interference member.

27. An optical interference electroluminescent device for displaying an image to a viewer in front of said device, comprising:

an anode layer;

a cathode layer, at least one of the anode layer and the cathode layer being substantially transparent to at least a portion of emitted electroluminescent light;

at least one organic electroluminescent layer disposed between said anode layer and said cathode layer, said electroluminescent layer having a first energy characteristic being the amount of energy required to extract an electron from a highest occupied molecular orbital of said electroluminescent layer, and a second energy characteristic being the amount of energy required to extract an electron from a lowest unoccupied molecular orbital of said electroluminescent layer; and

at least one optical interference member disposed between two of said layers, and having a work function substantially equal to said first energy characteristic when said optical interference member is between said anode and said electroluminescent layer, and having a work function substantially equal to said second energy characteristic when said optical interference member is between said cathode and said electroluminescent layer, said optical interference member being of a thickness and material such that the spectral reflectance of said electroluminescent device is so modified that the reflectance of ambient light by said electroluminescent device towards said viewer is reduced.

28. An electroluminescent device to emit light in a selected spectrum, comprising:

an anode layer

-23-

a cathode layer, one of said anode layer and said cathode layer being substantially transparent to at least a portion of said selected spectrum emitted by said electroluminescent device;

an organic electroluminescent layer between said anode layer and said cathode layer, said electroluminescent layer having a highest occupied molecular orbital respective to said anode layer and having a lowest unoccupied molecular orbital respective to said cathode layer; and

an optical interference member having a selected work function and operable to reduce ambient light reflected through said transparent layer, said optical interference member being between said electroluminescent layer and one of said anode layer and said cathode layer, wherein the difference between said selected work function and an energy level required to extract an electron from a respective molecular orbital approaches zero.

29. A method of fabricating an electroluminescent device for displaying an image to a viewer in front of said device, comprising the steps of:

depositing an anode layer onto a substrate;

depositing an organic electroluminescent layer onto said anode layer, said electroluminescent layer having a first energy characteristic associated with an anode side, and a second energy characteristic associated with a cathode side;

depositing an optical interference member onto said electroluminescent layer, said optical interference member for reducing the reflectance of ambient light towards said viewer, said optical interference member having a work function substantially equal to said second energy characteristic;

depositing a cathode layer onto said optical interference member; and
sealing said device.

30. A method of assembling an electroluminescent device for displaying an image to a viewer in front of said device, comprising the steps of:

depositing an anode layer onto a substrate;

-24-

depositing an optical interference member onto said anode layer; said optical interference member for reducing the reflectance of ambient light towards said viewer, said optical interference member having a work function;

depositing an organic electroluminescent layer onto said interference member, said electroluminescent layer having an energy characteristic being the amount of energy required to extract an electron from said electroluminescent layer, said energy characteristic being substantially equal to said work function;


depositing a cathode layer onto said electroluminescent layer; and
sealing said device.

31. A method of displaying an image to a viewer comprising the steps of:
emitting light from an organic electroluminescent layer between an anode and a cathode, said electroluminescent layer having a first energy characteristic respective to said anode and a second energy characteristic respective to said cathode; and

receiving ambient light incident towards said electroluminescent layer;
and

forming destructive interference from said ambient light at the incident surface of an optical interference member, said optical interference member having a selected work function and disposed between said electroluminescent layer and one of said anode and said cathode, the difference between said work function and a respective energy characteristic approaching zero.

1/1



INTERNATIONAL SEARCH REPORT

Int. Application No

PCT/CA 00/00849

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 H01L51/20 H05B33/22

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 H01L H05B

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

INSPEC, EPO-Internal, PAJ

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 12, 26 December 1996 (1996-12-26) -& JP 08 222374 A (IDEMITSU KOSAN CO LTD), 30 August 1996 (1996-08-30)	1, 10-12, 15, 24-31
A	paragraphs '0001!-'0009!	2-9
X	PATENT ABSTRACTS OF JAPAN vol. 1996, no. 05, 31 May 1996 (1996-05-31) -& JP 08 008065 A (TOPPAN PRINTING CO), 12 January 1996 (1996-01-12)	1, 12, 21, 23, 27-29, 31
A	paragraphs '0016!-'0062!	2-9, 24, 25
	--- -/--	

☒ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier document but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

"&" document member of the same patent family

Date of the actual completion of the international search

15 November 2000

Date of mailing of the international search report

22/11/2000

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax: (+31-70) 340-3016

Authorized officer

van der Linden, J.E.

INTERNATIONAL SEARCH REPORT

Int. l. Application No

PCT/CA 00/00849

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	PARTHASARATHY G ET AL: "A metal-free cathode for organic semiconductor devices" APPLIED PHYSICS LETTERS, APR 1998, vol. 72, no. 17, pages 2138-2140, XP000754419 ISSN: 0003-6951	1-5, 10-14, 16,17, 19, 23-25,29
A	the whole document	6-9,15, 26,30
X	EP 0 838 976 A (TDK CORP) 29 April 1998 (1998-04-29)	1-5, 10-13, 16,19, 21-25, 27,29,31
A	the whole document	6-9,14, 15,17, 28,30
A	US 5 049 780 A (DOBROWOLSKI J ET AL) 17 September 1991 (1991-09-17) cited in the application the whole document	1,13,14, 16-18, 21-23
A	GYOUTOKU A ET AL: "Organic EL dot-matrix display using carbon underlayer" SYNTHETIC METALS, MAY 1997, vol. 91, no. 1/03, pages 73-75, XP000890057 ISSN: 0379-6779 the whole document	1,6-9, 15,30
A	WO 97 38452 A (CAMBRIDGE DISPLAY TECH) 16 October 1997 (1997-10-16) the whole document	1,27,28, 31
P,X	WO 00 35028 A (CAMBRIDGE DISPLAY TECH) 15 June 2000 (2000-06-15)	1-19, 21-25, 27-31
P,A	the whole document	20,26

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PCT/CA 00/00849

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
JP 08222374 A	30-08-1996	JP 2931229 B	09-08-1999
JP 08008065 A	12-01-1996	NONE	
EP 0838976 A	29-04-1998	JP 10125469 A	15-05-1998
		US 5969474 A	19-10-1999
US 5049780 A	17-09-1991	CA 1302547 A	02-06-1992
		AT 141035 T	15-08-1996
		DE 68926906 D	05-09-1996
		DE 68926906 T	27-02-1997
		EP 0372763 A	13-06-1990
		JP 2276191 A	13-11-1990
		JP 2529741 B	04-09-1996
WO 9738452 A	16-10-1997	GB 2316228 A	18-02-1998
WO 0035028 A	15-06-2000	AU 1573500 A	26-06-2000